

Product Data Sheet

Product : Quadrant Polypenco Korea Acetron® ESD POM, Unfilled, Porosity-free copolymer acetal, extruded

Categories : Polymer; Thermoplastic; Acetal(POM); Acetal Copolymer; Unreinforced

Material Notes : Semitron ESD POM is part of the Quadrant family of products designed for use in the semiconductor industry, where electrostatic dissipation is a requirement. It is an extruded, static dissipative acetal that has mechanical performance to 225°F, high surface resistivity, and broad chemical resistance.

Properties	Units	Test Methods	Acetron® ESD POM
Physical Properties			
Specific Gravity	g/cc	ASTM D 792	1.31
Water Absorption, Immersion, 24hr	%	ASTM D 570(2)	2.0
Water Absorption at Saturation, Immersion	%	ASTM D 570(2)	8.0
Mechanical Properties			
Rockwell Hardness, M	M scale	ASTM D 785	-
Rockwell Hardness, R	R scale	ASTM D 785	105
Hardness, Shore D	D	ASTM D 2240	-
Tensile Strength	MPa	ASTM D 638	41.4
Tensile Modulus	GPa	ASTM D 638	1.36
Elongation at Break	%	ASTM D 638	32
Flexural Yield Strength	MPa	ASTM D 790	42.9
Flexural Modulus	GPa	ASTM D 790	1.28
Compressive Strength	MPa	10% Def.; ASTM D 695	55.2
Compressive Modulus	GPa	ASTM D 695	1.21
Shear Strength	MPa	ASTM D 732	41.4
Coefficient of Friction; Dry vs. Steel	-	QTM 55007	0.29
K (wear) Factor	mm ³ /N-M	QTM 55010	60.4 x 10 ⁻⁸
Limiting Pressure Velocity; 4:1 safety factor	MPa-m/sec	QTM 55007	0.0701
Izod Impact, Notched	J/cm	ASTM D 256	171
Electrical Properties			
Surface Resistivity per Square	Ω	EOS/ESD S11.11	10 ⁶ ~10 ⁸
Dielectric Constant	-	ASTM D 150	4.31 @Frequency 1e+6 Hz

Dielectric Strength; Short term	kV/mm	ASTM D 149	-
Dissipation Factor	-	ASTM D 150	0.036 @Frequency 1e+6 Hz

Thermal Properties

Coefficient of Thermal Expansion; CTE, linear	µm/m-°C	ASTM E 831	167 @Temperature -40.0 - 149 °C
Thermal Conductivity	W/m-K	ASTM F 433	-
Melting point ; Crystalline, Peak	°C	ASTM D 3418	160
Maximum Service Temperature, Air	°C	Long Term	82.2
Deflection Temperature at 1.8 Mpa (264psi)	°C	ASTM D 648	107
Flammability, UL94 ; 1/8inch(Estimated Rating)	-	-	HB

Compliance Property

Comments

3A-Dairy	No
Canada AG	No
FDA	No
NSF	No
USDA	No
RoHS	-

Descriptive Properties

Color	Natural / Black
Machinability	1-10, 1=Easier to Machine 1

Chemical Resistance Properties

Acid, Strong (pH1-3)	Unacceptable
Acids, Weak	Limited
Alcohols	Acceptable
Alkalies, Weak	Acceptable
Alkalies, Strong (pH 11-14)	Unacceptable
Chlorinated Solvent	Limited
Conductive / Static Dissipative	Yes
Continuous Sunlight	Limited
Hot Water / Steam	Limited
Hydrocarbons – Aliphatic	Acceptable
Hydrocarbons – Aromatic	Acceptable
Inorganic Salt Solution	Acceptable

Ketones, Esters

Acceptable

Miscellaneous Properties

Targeted Usage

Load + Bearing

All information supplied by or on behalf of Polypenco Korea in relation to its products, in any form, is supported by research and believed to be reliable, but Polypenco Korea assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Polypenco Korea for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.